

Technical sheet

Ecosoft

European Bovine leather, chrome tanning and a finish with pigments and resins.

Origine hides	European	
Average size	4,5 m2	
Thickness	1,1-1,2 mm	
UNI EN ISO 11640:1998		
Colour fastness to rubbing	500 cycles dry	≥ 4 grey scale
	250 cycles wet	≥ 4 grey scale
	80 cycles sweat	≥ 4 grey scale
UNI EN ISO 5402		
Flexing Endurance	No damage	
ISO 3377-1		
Tear resistance	≥20 N	
UNI EN ISO 11644		
Finish Adhesion - dry	≥ 2	
UNI EN ISO105-B02		
Colour fastness to artificial light	≥ 5 blue scale	

This leather comply with the strict regulations and EU Directives covering the use and presence of PCP, CFC, Chromo (VI) and Azo dyestuffs during the tanning process. Values indicated refer to the leather at the time of supply. Due to the natural properties of leather color variations between hides & one dye lot and another may occur.

The General Conditions of Ropelli B.V. (which are registred at Chamber of Commerce NL reg. nr. 64778010) apply on all our conventions. In particular (article 7), Client is responsible for having established whether the products meet the requirements arising from the intended use by Client. The values in this technical sheet are not a warranty in legal sense.